

# AQUAPROOF LIQUID

**Polymerbased coating that after application dries to a flexible membrane with high crackbridging properties, for the watertightness of surfaces not submitted to continuous waterpressure.**



## PRODUCTDESCRIPTION

AQUAPROOF LIQUID is a solvent free polymer based coating which is applied by airless, roller or paintbrush and dries to a watertight elastic membrane. AQUAPROOF LIQUID is used for the waterproofing of surfaces which are not continuously submitted to water contact, water pressure nor to rising humidity/damp.

AQUAPROOF LIQUID is fit for use both on horizontal and vertical surfaces for the waterproofing of:

- » Building foundations
- » Floors in wet rooms and balconies under cementbased screeds
- » Facades as waterproof membrane before installing the façade panels

AQUAPROOF LIQUID can be applied on the following surfaces: concrete, bricks, cement based coatings and plasters, silicate stone, plywood (or other type of woodpanels) for exterior use. For applications of AQUAPROOF LIQUID on plaster boards or other plasterbased materials, natural stone, etc. consult with the technical service of Hevadex.

AQUAPROOF LIQUID cannot be applied on surfaces containing bitumen.

## APPLICATION

### PREPARATION WORKS BEFORE APPLYING AQUAPROOF LIQUID

- » Ensure the surfaces to be sealed are dust free: remove loose or flaking material, surface efflorescence and standing water and all other kinds of pollutions that may affect adhesion.
- » Verify that the surfaces are dry and solid.
- » Close all gaps and joints with a width > 1mm with a fast set cement based repair mortar.
- » Applying on existing tile floors is possible, providing they are well adhering and roughened prior to application of AQUAPROOF LIQUID.
- » Apply Primer 43 on porous surfaces.
- » Temperature during application and drying of AQUAPROOF LIQUID: > 5°C.

### HOW TO APPLY AQUAPROOF LIQUID


- » Mix AQUAPROOF LIQUID before use; do not dilute with water or solvents.
- » Apply AQUAPROOF LIQUID with airless machine, roller or paintbrush; in two layers, first layer crosswise and after setting of the first layer.
- » Total minimum consumption: 1 kg/m<sup>2</sup> which is 1000 micron wet thickness. Wet thickness needs to be verified with a wet film gauge. Also verify visually on complete coverage.
- » In case of inside applications, allow ventilation for optimal curing.
- » Cleaning tools after application: with water.
- » AQUAPROOF LIQUID is resistant to minor chloor and calcium concentrations in water as well as to standard domestic cleaning products.
- » Finishing on AQUAPROOF LIQUID:
  - Await complete drying before applying a finish layer on AQUAPROOF LIQUID membrane such as floor tiles or façade panels;
  - Complete drying time depending environmental conditions: 3 days (indicative).



# AQUAPROOF LIQUID

**CARACTERISTICS**

- » Appearance: grey liquid
- » Density (g/cm<sup>3</sup>): 1,2
- » pH: 9,0
- » Solids (%): >50%
- » Elongation at break (DIN 53504) (%): >250
- » VOC: < 5ppm
- » Resistant to -30°C up to 100°C (after curing)

TESTINSTITUTE	TEST	STANDARD	VALUE
	Adhesion	ISO4624 (2016)	1,7 N /mm <sup>2</sup>
	Adhesion after watercontact	NBN EN 14891 (2012)	≥ 0,5 N/mm <sup>2</sup>
	Adhesion after ageing		
	Adhesion after contact with alcalin water		
	Adhesion after frost/defrost cycles		
	Water tightness		Pass
	Water absorption		Pass
	Crack bridging		Pass.

**PACKAGING**

10kg pails ; pallet: 44 x 10kg

**STORAGE**

24 months; original and closed packaging, 5 – 25°C.

**SAFETY**

Consult the safety data sheet prior to application.

DATE OF THIS EDITION: 30/05/2019

Our general conditions of sale apply. This document does not have a contractual value. This technical data sheet replaces and annuls the previous edition. The information given in this sheet has the purpose to inform and advice you. Hevadex bvba reserve the right to amend or change this information without notice. All information is given in good faith and without any warranty. The application, use and processing of these products are beyond our control and therefore the entire responsibility of the user/client/applicator. The user of the product must test the product's suitability and apply for the intended purpose. Established liability if any for any reason is always limited to the value of the goods supplied by EMDEX bvba. The products and systems are manufactured under total quality management. EMDEX bvba reserves the right to change the properties of its products. Users must always refer to the most recent issue of the local Product Data Sheet, copies of which will be supplied on request.